# PRODUCT DATA SHEET TACFIUX® 089HF

#### Introduction

**TACFlux® 089HF** is a no-clean flux formulated for SnAgCu and SnAg solders (also compatible with Sn/Pb solder). **TACFlux® 089HF** provides excellent wetting in air or nitrogen atmospheres. The flux and flux residue is halogen-free.

#### **Properties**

Test	Result
J-STD-004 (IPC-TM-650)	
Flux Type Classification	ROLO
Flux-Induced Corrosion (Copper Mirror)	Type L
Presence of Halide: Silver Chromate Fluoride Spot Test Cl Equivalent	Pass Pass <0.0%
Post-Reflow Flux Residue (ICA Test)	~35%
SIR	Pass
Bellcore Electrochemical Migration	Pass
Viscosity (C & P)	10kcps (Cone & Plate viscosity @ 5 minutes)
Tack	120 grams
Additional Test Results	
Appearance	Light Yellow–Amber
Maximum Reflow Temperature	260°C
Reflow Atmosphere	Nitrogen or Air
Shelf Life	1 year
Storage Condition	Stored @ 0–30°C (tip down for syringe/cartridge)

All information is for reference only.

Not to be used as incoming product specifications.

### Packaging

**TACFlux® 089HF** is available in 10 and 30cc syringes or 100g jars; however, other packaging can be provided to meet specific requirements.

## Cleaning

**TACFIux® 089HF** is designed for no-clean applications. If necessary, the flux can be removed by using a commercially available flux cleaner.

#### Reflow

Peak reflow temperature should be <260°C in an air or nitrogen atmosphere.

#### Storage

TACFlux® 089HF syringes and cartridges should be stored tip down at 0–30°C. If refrigerated, TACFlux® 089HF should be thawed for 4 hours at room temperature before using.

# **Technical Support**

Indium Corporation's internationally experienced engineers provide in-depth technical assistance to our customers. Thoroughly knowledgeable in all facets of Material Science as it applies to the electronics and semiconductor sectors, Technical Support Engineers provide expert advice in solder preforms, wire, ribbon, and paste. Indium Corporation's Technical Support Engineers provide rapid response to all technical inquiries.

#### **Safety Data Sheets**

The SDS for this product can be found online at http://www.indium.com/sds

This product data sheet is provided for general information only. It is not intended, and shall not be construed, to warrant or guarantee the performance of the products described which are sold subject exclusively to written warranties and limitations thereon included in product packaging and invoices. All Indium Corporation's products and solutions are designed to be commercially available unless specifically stated otherwise.

# From One Engineer To Another<sup>®</sup>



Contact our engineers: askus@indium.com Learn more: www.indium.com



ASIA +65 6268 8678 • CHINA +86 (0) 512 628 34900 • EUROPE +44 (0) 1908 580400 • USA +1 315 853 4900