PRODUCT DATA SHEET

Indium12.8HF

SnPb Solder Paste

Introduction

Indium12.8HF is a no-clean, halogen-free solder paste specifically formulated to accommodate fine-feature printing, as seen with 01005 and 008004 components. It also has high slump resistance allowing for cutting edge assemblies to minimize part spacing without bridging challenges. **Indium12.8HF** offers unprecedented stencil print transfer efficiency to work in the broadest range of processes to boost SPI yields. In addition, it is one of the lowest voiding pastes with a wide variety of area array packages and bottom terminated components.

Features

- Halogen-free per EN14582 test method
- High transfer efficiency and exceptional SPI yield with fine-feature apertures (01005, 008004)
- Eliminates hot and cold slump
- Low BGA, CSP, LGA, and QFN voiding
- One of our most stable pastes
- High oxidation resistance to eliminate graping

Alloys

Indium Corporation manufactures low-oxide spherical powder composed of a variety of Pb containing alloys that cover a broad range of melting temperatures. Type 5, Type 6, and Type 7 powder as standard offerings with Pb containing alloys. The metal percent is the weight percent of the solder powder in the solder paste and is dependent upon the powder type and application. Standard product offerings are detailed in the following table.

Standard Product Specifications

Alloy	Metal Load* (Types 5, 6, and 7)
SnPb/SnPbAg	87–91%

**The optimal metal loads are shown above. These can vary based upon geographic location and application/process needs.*

BELLCORE and J-STD Tests & Results

Industry Standard Test Results and Classification			
Flux Classification	ROL0	Typical Solder Paste Viscosity for SnPb T5-MC (Poise)	1,750
Based on the testing required by IPC J-STD-004D		Conforms with all requirements from IPC J-STD-005B	
Halogen-free per IEC 61249-2-21, Test Method EN14582	<900 ppm Cl <900 ppm Br <1,500 ppm Total		

All information is for reference only.
Not to be used as incoming product specifications.

Compatible Products

- **Rework Flux**: TACFlux® 089HF, TACFlux® 020B-RC
- **Cored Wire**: CW-807
- **Wave Flux**: WF-9945, WF-9958

Note: Other products may be applicable. Please consult one of Indium Corporation's Technical Support Engineers.

Storage and Handling Procedures

Refrigerated storage will prolong the shelf life of solder paste. Solder paste packaged in syringes and cartridges should be stored tip down.

Packaging	Storage Conditions (unopened containers)	Shelf Life
Syringe	1–10°C	3 months
Syringe	-20°C–0°C	6 months
Jar/Cartridge	1–10°C	6 months

Solder paste should be allowed to reach ambient working temperature prior to use. Generally, paste should be removed from refrigeration at least 2 hours before use. Actual time to reach thermal equilibrium will vary with container size. Paste temperature should be verified before use. Jars and cartridges should be labeled with date and time of opening.

Packaging

Indium12.8HF is currently available in 500g jars or 600g cartridges. Packaging for enclosed print head systems is also readily available. Alternate packaging options may be available upon request.

From One Engineer To Another®

INDIUM® CORPORATION®

PRODUCT DATA SHEET

Indium12.8HF SnPb Solder Paste

Printing

Stencil Design:

Electroformed and laser cut/electropolished stencils produce the best printing characteristics among stencil types. Stencil aperture design is a crucial step in optimizing the print process. The following are a few general recommendations:

- Discrete components—A 10–20% reduction of stencil aperture has significantly reduced or eliminated the occurrence of mid-chip solder beads. The "home plate" design is a common method for achieving this reduction.
- Fine-pitch components—A surface area reduction is recommended for apertures of 20mil pitch and finer. This reduction will help minimize solder balling and bridging that can lead to electrical shorts. The amount of reduction necessary is process-dependent (5–15% is common).
- For optimum transfer efficiency and release of the solder paste from the stencil apertures, industry standard aperture and aspect ratios should be adhered to.

Printer Operation

Solder Paste Bead Size	~20–25mm in diameter
Print Speed	25–150mm/second
Squeegee Pressure	0.018–0.027Kg/mm of blade length
Underside Stencil Wipe	Start at once per every 5 prints and decrease frequency until optimum value is reached
Squeegee Type/Angle	Metal with appropriate length / ~60 degrees
Separation Speed	5–20mm/second or per equipment manufacturer's specifications
Solder Paste Stencil Life	Up to 12 hours (at 30–60% RH and 22–28°C)


Cleaning

Indium12.8HF is designed for no-clean applications; however, the flux can be removed, if necessary, by using a commercially available flux residue remover.

Stencil Cleaning is best performed using isopropyl alcohol (IPA) as a solvent. Most commercially available stencil cleaners work well.

Reflow

Recommended Profile:



This profile is designed for use with Sn63/Pb37 and Sn62/Pb36/Ag2 and can serve as a general guideline in establishing a reflow profile for use with other alloys. Adjustments to this profile may be necessary based on specific process requirements. Start with the linear profile, then move to the optional soak profile, if needed.

Reflow Profile Details	SnPb Parameters		Comments
	Recommended	Acceptable	
Ramp Profile (Average Ambient to Peak) —not the same as maximum rising slope	0.5–1°C/sec	0.5–2.5°C/sec	To minimize solder balling, beading, hot slump
Soak Zone Profile (optional)	30–90sec	30–120sec	May minimize BGA/CSP voiding
	140–150°C	130–170°C	
Time Above Liquidus (TAL)	45–60sec	30–100sec	Needed for good wetting/reliable solder joint As Measured with thermocouple
Peak Temperature	198–213°C	195–233°C	
Cooling Ramp Rate	2–6°C/sec	0.5–6°C/sec	Rapid cooling promotes fine grain structure
Reflow Atmosphere	Air or N_2		N_2 can aid with material performance on small components

All parameters are for reference only.
Modifications may be required to fit process and design.

This product data sheet is provided for general information only. It is not intended, and shall not be construed, to warrant or guarantee the performance of the products described which are sold subject exclusively to written warranties and limitations thereon included in product packaging and invoices. All Indium Corporation's products and solutions are designed to be commercially available unless specifically stated otherwise.

All of Indium Corporation's solder paste and preform manufacturing facilities are IATF 16949:2016 certified.
Indium Corporation is an ISO 9001:2015 registered company.

Contact our engineers: askus@indium.com
Learn more: www.indium.com
ASIA +65 6268 8678 • CHINA +86 (0) 512 628 34900 • EUROPE +44 (0) 1908 580400 • USA +1 315 853 4900

©2026 Indium Corporation